

PRODUCT SPECIFICATION

DATE: 20.09.2008

PRODUCT NAME: ANTELOPE XXX

APPLICATION AREA: UPHOLSTERY

COMPOSITION: % 17 Polyester, % 28 Polyamide, % 9 Cotton, % 46 Acrylic

TEST TYPES	UNIT	WARP	WEFT	TEST METHOD
TENSILE STRENGTH	N	>350	>350	ISO 13934- 2
TEAR STRENGTH	N	>20	>20	ISO 13937-2
ABRASION RESISTANCE	cycles	>75000		ISO 12947
COLOR FASTNESS OF LIGHT	blue wool	4 / 5		ISO 105-B02
WEIGHT	gr / m ²	500 ± 13		ISO 2286 - 2
RUBBING FASTNESS	-	Wet min.4 - Dry min.4		ISO105-X12
EASY CLEAN	-	YES / EVET		-
WIDTH	cm	141 ± 1		-
ROLL LENGTH	m	35 ± 5		-

CLEANING INSTRUCTIONS

Liquid Stains: Blot the liquid stain gently with a high-absorbent material. Pat dry the area gently with a dry material to remove the remaining humidity (cotton cloth, paper towel, etc....). If the stain from the spill remains, remove the stain with a soapy cloth without diffusing the stain. After each rubbing motion, refresh the clean soapy cloth in order to prevent soiling.

Solid Particles: Remove the excess soiling with ultimate care without diffusing. Remove the solid particle from the fabric surface with the help of a soft spatula. To remove dust, use a vacuum cleaner or a soft brush. The remaining stains should be removed by rubbing with a soapy cloth in circular motion.

Ball-point pen and similar difficult stains : Dampen a clean cotton cloth in a white soap solution. Rub the stain off gently. Clean the surface with the damp cloth and leave the fabric for drying

Alcohol derives, Petroleum and alkali based solvents should not be used for cleaning. After all cleaning processes, the drying should be done with a low temperature blow dryer in large circular motion or the fabric should be left for natural drying. After drying, misoriented and damaged piles should be fixed with a soft brush.



This is Valid For All Colours Of The Product